

## TECHNICAL SHEET

25.05.2022 REV.0

### ANTIFOULING WHITE, GREY, BLACK

#### DESCRIPTION AND CHARACTERISTICS

High antifouling power, offer excellent coverage.

It can be used on all types of hulls, even in aluminum, because the copper salt contained does not create galvanic couples.

The product is suitable for boats with speeds over 30 knots.

<b>BINDER TYPE</b>	Resins-Acrylic copolymer
<b>COLOUR</b>	White-Grey-Black
<b>GLOSS LEVEL</b>	5-15 Gloss (60°)
<b>CAN PRESSURE</b>	From 4.2 to 4.8 Bar at 20 °C From 7.6 to 8.4 Bar at 50 °C
<b>DRYING TIME</b> (into air at 20 °C)	Dust free      10-20 min. Touch dry      30-60 min.
<b>OVERCOATING TIME</b>	8-12 hours minimum (20 °C)
<b>IMMISSION IN THE WATER</b>	24-48 hours minimum
<b>SPREADING CAPACITY</b>	From 0.7 to 1 m <sup>2</sup> for a 400 ml can.
<b>STORAGE</b>	Fresh and ventilated place.

#### USAGE

**Before use, carefully read the directions on the packaging and act accordingly.**

The surface of application must be perfectly clean, dry, degreased, and free from rust particles.

Before use shake well the can at last two minutes. Spraying covering layers at a distance of 25 cm.

#### N.B.

The above information covers at best our knowledge, but are not vinculating.

THE LABORATORY/SGQ